



PREPARATION AND APPLICATION PROCEDURE

CONCRETE GARAGE FLOOR

PREPARATION	FINISH	SEALANT
<p>Procedure:</p> <ul style="list-style-type: none"> - If the surface is covered with paint or sealant, remove paint using a sandblaster, a diamond grinder or any other appropriate means. - Clean the surface with a 3500 lb., rotary, jet pressure washer, gasoline motor. (Available at tool rental centers.) - Dilute TexNov Concrete Conditioner 50% with water in a clean separate container. - The concrete surface must be wet when applying TexNov Concrete Conditioner. - Apply the Concrete Conditioner mixture to the surface with a sprayer and leave on for 10 to 15 minutes as needed. Thoroughly brush the surface thoroughly and rinse thoroughly with a pressure washer. - If the solution dries out because of the delay or hot weather, starting again with a simple rinse will not suffice. - Let the surface dry for 48 hours of good weather. - Repair cracks with TexNov All Purpose Polymer or TexNov 200. - Allow the surface to dry for 24 hours. - Apply a layer of TexNov General Purpose Polymer OR TexNov 200 before the application of the finishing coat. - Allow the surface to dry for 24 hours. <p>Important:</p> <ul style="list-style-type: none"> - Remove any accessories such as ramps, furniture, stairs that could be damaged when applying the above mentioned products. - Properly protect fixed surfaces (doors, windows, building coverings, rods and pieces of metal, etc.) with polythene or other suitable protective means - for a very contaminated concrete surface use the TexNov Surface Cleaner and continue with TexNov Concrete Conditioner to prepare the surface to receive a finish. TexNov Concrete Conditioner also helps to dissolve surface rust. 	<p>Procedure:</p> <ul style="list-style-type: none"> - Apply a first coat of TexNov Acrylic Coating. Use a brush and / or a 10 mm roller - Let dry 24 hours. - Apply a second coat of TexNov Acrylic Coating. Use brush or roller with bristles 10 mm - Let dry 24h. <p>Note: In hot weather dilute with water (50 ml / liter) for ease of application.</p>	<p>Procedure:</p> <ul style="list-style-type: none"> - Apply 2 coats of TexNov Met-30 Sealant (acrylic sealant). Use brush or roll 10 mm. Leave 24 hours between each layers. - Allow the surface to dry for 24 hours before stepping on it. - Allow the surface to dry for 72 hours in good weather before reinstalling furniture and fixtures <p>Note:</p> <ul style="list-style-type: none"> - On a vertical surface, sealant is not required. - TexNov Met-HD Sealant also recommended on a concrete floor where there is no acrylic, as well as a surface that requires greater strength. <p>Important: A 30 day delay is required before entering a vehicle.</p>

Maintenance: Clean the surface with the **TexNov Surface Preparer** (6 water / 1 Preparer). Let dry and add a coat of **Met-HD** Sealant every 3 years or as needed, which should enable you to keep your surface in good condition.

