



PREPARATION AND APPLICATION PROCEDURE

SOFTWOOD

PREPARATION	SEALANT	FINISH	SEALANT
<p>Procedure:</p> <ul style="list-style-type: none"> - Thoroughly rinse the surface with a 2000-pound pressure washer. - Clean with Texnov Surface Cleaner undiluted or diluted 1:1. - Brush the surface and leave for 15 to 30 minutes. - Rinse the surface thoroughly with a pressure washer. - Make a good sanding to make the surface rough with sand paper 60 grit. - Let the surface dry for 48 hours of good weather. 	<p>Procedure:</p> <ul style="list-style-type: none"> - TexNov Met-30 sealant should be applied over the entire surface of some softwood substrates prior to the installation of the finish coat. Example: Pine, Cedar, Spruce - Allow the surface to dry for 24 hours. 	<p>Procedure:</p> <ul style="list-style-type: none"> - In warm weather dilute with water (50 ml / liter) for ease of application. - You can fill the screw heads with TexNov Acrylic Coating. (screws must be rustproof: zinc, ceramic). - Apply 2 coats of TexNov Acrylic Coating. Use brush or roller with 10 mm bristles. (24h between each layer). - Allow the surface to dry for 24 hours. <p>Note: TexNov Acrylic Coating will not hide any defects due to unevenly installed substrate.</p>	<p>Procedure:</p> <ul style="list-style-type: none"> - Apply 2 coats of Met-30 Sealant. Use a brush or roller with 10 mm bristles (24 hours between each coat). - Let the surface dry for a 24-period of good weather. <p>Note: All wood surfaces located less than 60" from the ground or poorly ventilated should ideally be sealed on all sides with Met-30 Sealant. This will prevent premature deterioration of the wood due to the migration of moisture from the ground to the sky.</p>

Maintenance: Clean the surface with **TexNov Surface Preparer** (6 water / 1 Preparer). Let dry and add a coat of **Met-30** Sealant every 3 years or as needed. This should enable you to keep your surface in good condition.

