



# PREPARATION AND APPLICATION PROCEDURE

## GALVANIZED OR PAINTED STEEL

| PREPARATION  | FINISH   | SEALANT   |
|--|--|---|
| <p><b>Procedure:</b></p> <ul style="list-style-type: none"> <li>- Rinse the surface well with a 2000 lb. pressure washer.</li> <li>- Apply and scrub the <b>TexNov Surface Preparer</b>.</li> <li>- Let act for 15 minutes by keeping the surface wet.</li> <li>- Rinse thoroughly with a pressure washer.</li> <li>- Let the surface dry for 24 hours prior to applying the finish coating.</li> </ul> <p><b>Note:</b> In places where there is rust, apply a primer to metal previously.</p> | <p><b>Procedure:</b></p> <ul style="list-style-type: none"> <li>- In warm weather dilute with water (50 ml/liter) for ease of application. <u>The temperature of the surface should not exceed 30° C at the application.</u></li> <li>- Apply 2 coats of <b>TexNov Acrylic Coating</b>. Use a brush or roller with 10 mm bristles (24 hours between applying each coat).</li> <li>- Let the surface dry for 24 hours.</li> </ul> | <p><b>Procedure:</b></p> <ul style="list-style-type: none"> <li>- To obtain a surface that will remain beautiful for a long time, apply <b>TexNov Met-30 Sealant</b> or <b>TexNov WRS-40 Sealant</b> for horizontal surfaces. Use a brush or a roller with 10 mm bristles or a sprayer.</li> <li>- Let the surface dry for 24 hours.</li> </ul> |

**Maintenance:** Clean the surface with **TexNov Surface Preparer** (6 water / 1 Preparer). Let dry and add a coat of **Met-30 Sealant** every 3 years or as needed. This should enable you to keep your surface in good condition.

