


PREPARATION AND APPLICATION PROCEDURE

REGULAR TREATED WOOD



PREPARATION

Procedure:

- Clean with the **Texnov Surface Cleaner** undiluted or diluted 1:1.
- Brush the surface and leave for 15 to 30 minutes.
- Rinse the surface thoroughly with a pressure washer on the surface with a 2000-pound pressure washer.
- Let the surface dry for 48 hours of good weather.
- You can fill in screw heads with **TexNov Acrylic Coating** (screws must be antirust: zinc, ceramic).
- Make a good sanding to make the surface rough (with sand paper 60).

Important:

- Heavily damaged and / or rotten wood must be replaced. We recommend a period of 12 to 18 months of treated wood drying (one or two summer seasons depending on the moisture content of the wood) before applying Tex Nov products for optimal results
- For optimum results, the moisture content of the wood must not exceed 15% humidity.

FINISH

Procedure:

In warm weather dilute with water (50 ml / liter) for ease of application.

- Apply 2 coats of **TexNov Acrylic Coating**. Use brush or roller with 10 mm bristles. (24h between each layer).
- Allow the surface to dry for 24 hours.

Note: **TexNov Acrylic Coating** will not hide any defects due to unevenly installed substrate.

SEALANT

Procedure:

- Apply 2 coats of Sealant **Met-30**. Use brush or roller with 10 mm bristles (24h between each layer).
- Allow the surface to dry for 24 hours.

Note: Any wood surface located less than 60 «from the ground or poorly ventilated should ideally be sealed on all sides with **Met-30** Sealant. This avoids premature deterioration of the wood due to the migration of moisture from the soil to the sky.

Maintenance: Clean the surface with **TexNov Surface Preparer** (6 water / 1 Preparer). Let dry and add a coat of **Met-30** Sealant every 3 years or as needed. This should enable you to keep your surface in good

TexNov

839 Joseph-Louis-Mathieu, Sherbrooke J1R 0X3
www.texnov.com - info@texnov.com
1 877 316-6388

The application instructions and performance characteristics are based on information we believe to be reliable. They are offered to the best of our knowledge, but without guarantee, as conditions and methods of use of our products are beyond our control.