

## GELNOV CHROMA

# Opaque semi-gloss acrylic interior / exterior coating

**GeINOV CHROMA** is a 100% acrylic exterior grade water-based coating giving a semi-gloss film that protects concrete, wood and waterproof surfaces (walls). **GeINOV CHROMA** is an opaque coating and sealant. This product is specially formulated for maximum outdoor resistance and is reduced in VOC to allow indoor application. **GeINOV CHROMA** can be used to refresh the color of other **TexNov** acrylic coatings.





## **GELNOV CHROMA**

Opaque semi-gloss acrylic interior / exterior coating

#### 1. DESCRIPTION:

**GeINOV CHROMA** is a 100% acrylic exterior grade water-based coating giving a semi-gloss film that protects concrete, wood and waterproof surfaces (walls). **GeINOV CHROMA** is an opaque coating and sealant. This product is specially formulated for maximum outdoor resistance and is reduced in VOC to allow indoor application. **GeINOV CHROMA** can be used to refresh the color of other **TexNov** acrylic coatings.

Characteristics	Advantages		
Excellent UV resistance, exterior grade pigments.	No yellowing, discoloration or cracking.		
100% acrylic resin.	<ul> <li>Hydrophobic (water pearl on the surface)</li> <li>Resistance to alkali, climate and superior aging.</li> <li>Flexibility and resistance to fouling without compromise. Non-sticky finish.</li> </ul>		
Air curing technology	<ul> <li>After a complete cure the gel has an increased resistance to scratches (floors).</li> <li>A hardness film comparable to the solvent-based product, in a water-based product.</li> </ul>		
Permeability of adequate vapors.	The surfaces breathe and the film does not scale.		
High resin content.	Excellent adhesion on multitude of substrates.		
Surfacing additives	<ul><li>Smooth surface and easy to clean.</li><li>High planning and resistance to the slides without compromise.</li></ul>		
Special formulation.	<ul> <li>Application by brush, roller, spray and squeegee.</li> <li>Fast drying without cracking (outside).</li> <li>Resistance to bacteria and fungi.</li> <li>Makes a semi-gloss opaque film.</li> </ul>		

#### 2. APPLICATION AND SUBSTRATE TYPE:

The surface to be coated must be dry, free from peeling paint, dust, oil, grease or any other pollutants. For an exemplary surface preparation use *TexNov* products to clean (Concrete Conditioner, Surface Cleaner).

A surface preparation is essential to obtain maximum adhesion. 100% acrylic coatings are recognized as being durable and durable in the outside (UV & weather) more than epoxy, polyurethane, styrene-acrylic, vinyl acrylic and alkyd paint.

The surface coated should be at a temperature of 5°C to 30°C protected from the sun and rain. After the application protect the surface from rain and bad weather for 36 hours. Allow to harden 78 hours before placing furniture or other heavy objects on the surface.

**GeINOV CHROMA** can be applied to different substrates: cement, concrete, wood, Masonite, gypsum, stucco, plaster, brick and all types of masonry. **GeINOV CHROMA** is a coating used as a finish coat for some of the Texnov Systems

#### 3. MESURES OF CAUTION:

**GeINOV CHROMA** will follow the profile of the surface. To obtain a smooth surface, it is necessary that the imperfections of the substrates first be corrected with a with the appropriate Texnov product.

A first layer of normal thickness followed by a second thicker layer will make it possible to obtain a highly smooth surface.

Dilution of *GelNOV CHROMA* with water is not recommended, as it will harm the opacity and adhesion of the film. No additives or accelerators should be added.

For more information on the handling, handling or use of this product, please consult our Material Safety Data Sheet or consult our Technical Service Department.



#### **4. PHYSICAL PROPERTIES:**

Solids :		32.0 %	
pH:		8.5-9.0	
		1.1	
Density:		1.1	
Viscosity with model Brookfield DV2T HA, spindle # H4 / 10 rpm :		12500 cps	
Water vapor permeability ASTM E-96:		> 570 ng/(Pa·s·m²) (> 10 perms)	
Glass transition temperature at mid-point / Tg (°C) :		30 before cure	
V.O.C. (Volatile Organic Compounds)		< 125g/L	
Recommended layer thickness		7.5 to 10 mils (2 layers are required)	
Surface capacity for 2 layers per 18.9L pall (20 Kg)		About 600 pi <sup>2</sup>	
Storage		Protect from cold and hot temperatures	
Durability		2 years	
Drying conditions	Dry to touch	2h	
	Ready for 2nd layer	4h	
	Walk on the surface	24h	
	Complete cure	14 days minimum	



Effective Date: 2011-01-15 - Revision Date: 2023-07-01

### **SAFETY DATA SHEET**

#### **SECTION 1 - IDENTIFICATION**

PRODUCT	COMPANY IDENTIFICATION
Name: Gelnov Chroma	TexNov inc.
<b>Description:</b> High performance colored overlay coating with a semi-gloss	839 Joseph-Louis-Mathieu
finish.	Sherbrooke, Québec, Canada J1R 0X3
<b>Restriction of use:</b> Sanding or grinding the dried product emits dangerous dust.	Emergency Phone Number: 1 877 316-6388

#### **SECTION 2 - HAZARD IDENTIFICATION**

#### **Pictograms**

None.

**Warning statements** 

None.

**Product classification** 

None.

**Hazard statements** 

None.

#### **Precautionary statements**

**Prevention:** Wear gloves and safety glasses. Use in a well-ventilated area. Inhalation of sanding dust or grinding of the dry product may be harmful. These dusts can cause irritation to the respiratory tract and can damage organs (lungs). This product contains ingredients that are considered carcinogenic if transformed into dust.

#### Intervention

**INGESTION:** Call Poison Control Center or doctor immediately. Do not induce vomiting unless advised by the doctor. EYES: Immediately flush with plenty of water for 15 minutes, occasionally lifting the eyelids. SKIN: wash with soap and water. Take off immediately all contaminated clothing. INHALATION: If person is not breathing, give artificial respiration and seek medical attention. If breathing is difficult, remove victim to fresh air.

**STORAGE** Store at 5 to 30°C in a closed plastic container. Keep away from frost.

**DISPOSAL:** Dispose of contents and container in accordance with local regulations.

#### SECTION 3 - COMPOSITION / INFORMATION ON INGREDIENTS

Ingredient	CAS number	% (weight/weight)
Titanium dioxide	13463-67-7	1-13

The titanium dioxide content of the product is considered encapsulated or embedded in the binder polymer and not bio-accessible by inhalation in normal use of the product. Based on current knowledge and applicable concentrations, there are no other ingredients in this product that are classified as hazardous by GHS and that should be reported in this section.

#### **SECTION 4 - FIRST AID MEASURES**

Eye contact: Immediately flush with plenty of water for 15 minutes, occasionally lifting the eyelids.

**Skin contact:** Wash with soap and water. Take off immediately all contaminated clothing.

**Ingestion:** Call Poison Control Center or doctor immediately. Do not induce vomiting unless advised by the doctor.

**Inhalation:** If person is not breathing, give artificial respiration and seek medical attention. If breathing is difficult, remove victim to fresh air.



Effective Date: 2011-01-15 - Revision Date: 2023-07-01

#### **SECTION 5 - FIRE-FIGHTING MEASURES**

Non-flammable product, but it may splash if heated above boiling point.

**Combustion product:** If the product is heated to combustion, after the release of water vapor, carbon oxides will be emitted. **Use the appropriate extinguisher.** 

#### **SECTION 6 - ACCIDENTAL RELEASE MEASURES**

Pick up all the dispersion with a shovel and eliminate the discards. Do not send the dispersion into the sewer, occurs can clog the piping.

#### **SECTION 7 - HANDLING AND STORAGE**

**Handling safety precaution:** Do not eat, smoke or drink in the work area. Wash hands after handling. Avoid contact with hands and eyes.

**Storage safety conditions:** Keep in a dry place away from frost and sunlight. The product may coagulate. The storage temperature is 5 to 30°C. Keep in a closed plastic container.

#### **SECTION 8 - EXPOSURE CONTROL / PERSONAL PROTECTION**

#### **CONTROL PARAMETERS:**

**Occupational Exposure Limits:** 

Breathable dust	RSST		ACGI	H TLV
Ingredient	VEMP DIVS		TWA	STEL
Titanium dioxide	Not available	5000 mg/m <sup>3</sup>	10mg/m³	Not available

RSST : Regulation respecting occupational health and safety; VEMP : Weighted average exposure value

DIVS: Immediate danger to life and health: ACGIH: American Conference of Governmental Industrial Hygienists

TLV : Threshold limit value; TWA : Time-weighted average; STEL : Short-terrm exposure limit

#### **Individual protection measures**

**Respiratory protection:** Wear appropriate respiratory protection if dusts / fumes / gases / mists / vapors / aerosols are possible above permissible limits. Use in a well ventilated place.

**Eye Protection:** To reduce exposure, wear safety glasses.

**Hand protection:** To reduce exposure, wear gloves. Wash your hands thoroughly after using the product. Do not eat, drink or smoke when handling this product.

#### **SECTION 9 - PHYSICAL AND CHEMICAL PROPERTIES**

Appearance: White gel.
Odor: Low odor of ammonia.
Odor threshold: Not available

pH: 8-9.

Freezing point: 0°C

Boiling point: 100°C.

**Evaporation rate:** Not available.

Flammability (solid and gas): Not applicable.

Explosive limit: Not applicable. Vapor pressure: Not available. Vapor density: Not available.

Relative density: 1,2.

**Solubility in water:** may be diluted with water.





Effective Date: 2011-01-15 - Revision Date: 2023-07-01

Partition coefficient n-octanol / water: Not available.

**Auto-ignition temperature:** Not applicable. **Decomposition temperature:** Not available.

Viscosity: 10000 mm<sup>2</sup>/s (converted from measurement on Brookfield).

#### **SECTION 10 - STABILITY AND REACTIVITY**

Chemical stability: This product is considered stable under recommended storage conditions.

**Reactivity:** Incompatible with strong oxidants and strong acids.

**Possibility of hazardous reactions:** This product can not polymerize.

Hazardous decomposition product: If the product is heated to combustion, there will be emission of carbon oxides.

#### **SECTION 11 - TOXICOLOGICAL INFORMATION**

Routes of entry: This product may be absorbed through the respiratory, digestive and cutaneous routes.

**Acute toxicity (calculated GHS):** 

Product	DL <sub>50</sub> oral, mg/kg	DL <sub>50</sub> cutaneous, mg/kg	CL <sub>50</sub> , mg/L
Gelnov Chroma	> 10000 (rat)	> 10000 (rabbit)	> 100 (rat)

**Skin irritation:** Virtually nil. An irritation of a mechanical nature is possible.

**Irritation of the eyes:** Not important. An irritation of a mechanical nature is possible.

Respiratory or skin sensitization: Virtually nil.

Specific target organ toxicity: None

**Carcinogenicity:** 

The sanding or grinding of this product is its dry form can produce particles of titanium dioxide which is considered carcinogens classified 2B according to IARC.

Ingredient	CIRC	ACGIH	NTP
Titanium dioxide	Group 2B	Group A4	N

CIRC: International Center for Research on Cancer. Group 2B: May be carcinogenic to humans. Group A4: Non-classifiable substance as a carcinogen to humans. NTP: National Toxicology Program; N: Negative.

Reproductive toxicity: none.

Germ cell mutagenicity: none.

#### **SECTION 12 - ECOLOGICAL INFORMATION**

**Ecotoxicology:** Not available.

Bioaccumulative potential: Not available. Volatile organic compounds (V.O.C.)  $\leq$  130g / L.

#### **SECTION 13 - DISPOSAL CONSIDERATIONS**

Dispose of releases in according to Municipal, Provincial and National Regulations.



839 Joseph-Louis-Mathieu, Sherbrooke J1R 0X3 www.texnov.com - info@texnov.com

1 877 316-6388



#### PRODUCT NAME: GELNOV CHROMA

Effective Date: 2011-01-15 - Revision Date: 2023-07-01

#### **SECTION 14 - TRANSPORT INFORMATION**

**Shipping Name:** Not Applicable. **TDG Classification:** Not Regulated.

#### **SECTION 15 - REGULATORY INFORMATION**

WHMIS 2015 Classification: None.

The product classification and SDS have been developed in accordance with the HPR.

#### **SECTION 16 - OTHER INFORMATION**

**SDS** prepared by: Texnov inc.

**Emergency telephone number:** 1-877-316-6388

**Revision Date: 2023-07-01** 

**Warning:** The information and recommendations contained in this document have been written to the best of knowledge and technical data collected by Texnov Inc. at the time of the revision. This document is intended to inform users of the product about the precautionary measures when using the product. No warranty is given on the properties mentioned on the products. No liability will be assumed for cases of misuse of the product or failure to observe the safety instructions contained in this document.

